

PRODUCT NAME: TRIPLEX

PRODUCT CODE: C/5

TEST PARTICULARS	OBTAINED VALUE
TOTAL THICKNESS	CENTRAL 0.16MM
SUBSTANCE G/M2	CENTRAL 228.04 MAXIMUM 229.45 MINIMUM 227.70
LAMINATION THICKNESS TOLERANCE	10%
UNFOLDED TENSILE STRENGTH (N/10MM MIN)	MD CMD
	165..3 89.6
FOLDED STRENGTH (N/10MM MIN)	MD CMD
FILM SIDE	127.2 87.7
ELONGATION UNFOLDED	MD CMD
	3.1 10.6
ELECTRIC STRENGTH IN AIR AT 27C BREAKDOWN VOLTAGE KV	AC 5.9

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1 ST FLOOR MUMBAI-400 002 (INDIA) FACTORY:
AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA N03, VILLAGE, WALIV, VASAI (E) DIST-
PALGHAR T. (022) 2208 4601 F.(022) 2206 3065 Email :jatinmodi63@gmail.



(022) 2208 5122

M. +919870774667

Web :www.jmodigroup.com



PRODUCT NAME: TRIPLEX

PRODUCT CODE: C/7

TEST PARTICULARS	OBTAINED VALUE
TOTAL THICKNESS	CENTRAL 0.20MM
SUBSTANCE G/M2	CENTRAL 250.2 MAXIMUM 253.8 MINIMUM 252.9
LAMINATION THICKNESS TOLERANCE	10%
UNFOLDED TENSILE STRENGTH (N/10MM MIN)	MD CMD
	180.8 118
FOLDED STRENGTH (N/10MM MIN)	
FILM SIDE	MD CMD
	136.4 88.9
ELONGATION UNFOLDED	MD CMD
	4.9 11.9
ELECTRIC STRENGTH IN AIR AT 27C	AC
BREAKDOWN VOLTAGE KV	5.9

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1 ST FLOOR MUMBAI-400 002 (INDIA) FACTORY:
AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA N03, VILLAGE, WALIV, VASAI (E) DIST-
PALGHAR T. (022) 2208 4601 F.(022) 2206 3065 Email :jatinmodi63@gmail.

(022) 2208 5122

M. +919870774667

Web :www.jmodigroup.com



PRODUCT NAME: TRIPLEX

PRODUCT CODE: C/10

TEST PARTICULARS	OBTAINED VALUE
TOTAL THICKNESS	CENTRAL 0.28MM
SUBSTANCE G/M2	CENTRAL 291.2 MAXIMUM 292.8 MINIMUM 285.9
LAMINATION THICKNESS TOLERANCE	10%
UNFOLDED TENSILE STRENGTH (N/10MM MIN)	
MD	209.8
CMD	131.3
FOLDED STRENGTH (N/10MM MIN)	
FILM SIDE	
MD	175.4
CMD	97.9
ELONGATION UNFOLDED	
MD	5
CMD	12.5
ELECTRIC STRENGTH AC IN AIR AT 27C BREAKDOWN VOLTAGE KV	6.4

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1ST FLOOR MUMBAI-400 002 (INDIA)
FACTORY: AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA NO3, VILLAGE, WALIV, VASAI (E) DIST-PALGHAR



T. (022) 2208 4601
(022) 2208 5122

F. (022) 2206 3065
M. +919870774667

Email : jatinmodi63@gmail.com
Web : www.jmodigroup.com

