


APA CLASS "F"

UC ARAMIDPAPER+POLYESTERFILM+UC ARAMID PAPER
(METALAM)



PROPERTY	UNITS	TEST METHOD	UC APA 2 2 2(0.31)
THICKNESS	MIC	IEC 60626-2:2009	310
THICKNESS TOLERANCE	+/-%	IEC 60626-2:2009	15
BASIC WT	GM/SQ.MT	IEC 60626-2:2009	170
BASIC WT TOLERANCE	(+/-12%)	IEC 60626-2:2009	12
YIELD	SQ.M/KG(+/-12%)	INTERNAL	5.88
TENSILE STRENGTH	N/10MM	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-75,CD-75/ MD-75,CD-75
ELONGATION	%(MIN)	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-8,CD-10
B.D.V	KV	IEC 60626-2:2009 (UNFOLDED/FOLDED)	6/5

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1ST FLOOR MUMBAI-400 002 (INDIA)
FACTORY: AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA NO3, VILLAGE, WALIV, VASAI (E) DIST-PALGHAR



T. (022) 2208 4601
(022) 2208 5122


F. (022) 2206 3065
M. +919870774667

Email : jatinmodi63@gmail.com
Web : www.jmodigroup.com



APA CLASS "F"

UC ARAMID PAPER+POLYESTER FILM+UC ARAMID PAPER
(METALAM)



PROPERTY	UNITS	TEST METHOD	UC APA 5 3 5(0.35)
THICKNESS	MIC	IEC 60626-2:2009	350
THICKNESS TOLERANCE	+/-%	IEC 60626-2:2009	15
BASIC WT	GM/SQ.MT	IEC 60626-2:2009	170
BASIC WT TOLERANCE	(+/-12%)	IEC 60626-2:2009	12
YIELD	SQ.M/KG(+/-12%)	INTERNAL	5.8
TENSILE STRENGTH	N/10MM	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-100,CD-100/ MD-80,CD-90
ELONGATION	%(MIN)	IEC 60626-2:2009 (UNFOLDED)	MD-8,CD-11
B.D.V	KV	IEC 60626-2:2009 (UNFOLDED/FOLDED)	10/8

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1ST FLOOR MUMBAI-400 002 (INDIA)
FACTORY: AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA NO3, VILLAGE, WALIV, VASAI (E) DIST-PALGHAR



T. (022) 2208 4601
(022) 2208 5122


F. (022) 2206 3065
M. +919870774667

Email : jatinmodi63@gmail.com
Web : www.jmodigroup.com



APA CLASS "F"

UC ARAMIDPAPER+POLYESTERFILM+UC ARAMID PAPER
(METALAM)



PROPERTY	UNITS	TEST METHOD	UC APA 2 4 2(0.37)
THICKNESS	MIC	IEC 60626-2:2009	370
THICKNESS TOLERANCE	+/-%	IEC 60626-2:2009	20
BASIC WT	GM/SQ.MT	IEC 60626-2:2009	240
BASIC WT TOLERANCE	(+/-12%)	IEC 60626-2:2009	12
YIELD	SQ.M/KG(+/-12%)	INTERNAL	4.16
TENSILE STRENGTH	N/10MM	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-125,CD-125/ MD-100,CD-100
ELONGATION	%(MIN)	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-7,CD-10
B.D.V	KV	IEC 60626-2:2009 (UNFOLDED/FOLDED)	10/9

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1ST FLOOR MUMBAI-400 002 (INDIA)
FACTORY: AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA NO3, VILLAGE, WALIV, VASAI (E) DIST-PALGHAR



T. (022) 2208 4601
(022) 2208 5122


F. (022) 2206 3065
M. +919870774667

Email : jatinmodi63@gmail.com
Web : www.jmodigroup.com



APA CLASS "F"

UC ARAMID PAPER+POLYESTER FILM+UC ARAMID PAPER
(METALAM)



PROPERTY	UNITS	TEST METHOD	UC APA 2 2 2(0.40)
THICKNESS	MIC	IEC 60626-2:2009	400
THICKNESS TOLERANCE	+/-%	IEC 60626-2:2009	20
BASIC WT	GM/SQ.MT	IEC 60626-2:2009	280
BASIC WT TOLERANCE	(+/-12%)	IEC 60626-2:2009	12
YIELD	SQ.M/KG(+/-12%)	INTERNAL	3.57
TENSILE STRENGTH	N/10MM	IEC 60626-2:2009 (UNFOLDED/FOLDED)	MD-140,CD-140/ MD-129,CD-129
ELONGATION	%(MIN)	IEC 60626-2:2009 (UNFOLDED)	MD-3,CD-10
B.D.V	KV	IEC 60626-2:2009 (UNFOLDED/FOLDED)	12/10

ADMIN OFF : 141, PRINCESS STREET, SAI BHUVAN, 1ST FLOOR MUMBAI-400 002 (INDIA)
FACTORY: AGRAWAL UDYOG NAGAR, BLDG. NO. 10, GALA NO3, VILLAGE, WALIV, VASAI (E) DIST-PALGHAR



T. (022) 2208 4601
(022) 2208 5122

F. (022) 2206 3065
M. +919870774667

Email : jatinmodi63@gmail.com
Web : www.jmodigroup.com

